

LAC 650 SL

Technical sheet

USES

Recommended use Pergolas, Terrace awnings, Sail shade, Marquees, Glamping, Flexible doors

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den							
Coating	PVC Lowick coating both side							
Finish	Cleangard lacquer both sides							
Weight	680				g/m ²	ISO 3801		
Width	250	250	250	300	300	300	cm	
Roll length	30	60	250	30	60	250	ml	

FABRIC RESISTANCE

Tensile strength	260	250	daN/5cm	NF EN ISO 1421
Tear strength	32	28	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-S2-D0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701
	CSFM Title19			CSFM Title 19

Values may vary in a tolerance of +/-10%.
Specification maybe modified and are subject to manufacturer's requisites.
Product compatibility to the application is reserved to the users' appraisal.
The buyer of our products is responsible for checking the validity of the above data.



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.

